# **3M**

# 3M<sup>™</sup> Scotchcast<sup>™</sup> Easy Dispenser 250 Electrical insulating, re-enterable resin



# 1. Product Description

3M™ Scotchcast™ Easy Dispenser 250 is an easy to use dispenser of electrical re-enterable resin for electrical installers. The 3M™ Scotchcast™ Easy Dispenser 250 contains 3M™ Scotchcast™ Resin 2123. This is a soft, two-part polybutadiene electrical resin encapsulant, designed for reenterable splice protection.

3M<sup>™</sup> Scotchcast<sup>™</sup> Resin 2123 is formulated for virtually every electrical application requiring a reliable, soft, re-enterable resin with good handling and performance characteristics. Scotchcast<sup>™</sup> Resin 2123 has good wetting properties and low viscosity. The resin flows well at low temperatures, filling the closure and minimising air voids.

3M Deutschland GmbH Carl-Schurz-Str.1 41453 Neuss Germany 

#### **Applications** 2.

3M™ Scotchcast™ Resin 2123 is used for electrical insulation and moisture sealing of multicore low voltage cables up to 0.6/1 (1.2) kV in junction boxes where a re-enterable system is required.

#### 3. **Typical Properties**

#### 3.1 **Physical and Electrical Properties**

Property		Value	Specification
Mixing ratio A:B Colour		1:1 Amber, Translucent	- -
Gel Time at 23 °C		40 min +/- 5 min	DIN 16945
Part A&B mixed Density		0.86 g/cm³	EN ISO 1183-1
Curing time	at 21 °C	24 hours	-
Part A&B cured* * curing and aging according to Cenelec HD631.1 S2			
Mechanical Prope Tensile strength	rties	0.04 Mpa	EN ISO 527
Elongation at break		31.6 %	EN ISO 527
Electrical propertic Volume resistivity	es at 23 °C at 80 °C	> 7 x 10 <sup>12</sup> Ωcm > 1 x 10 <sup>11</sup> Ωcm	HD 429 HD 429
Dielectric Strength	at 23 °C	22 kV/mm	EN 60243-1
Dissipation factor	at 23 °C at 80 °C	0.03 0.1	IEC 60250 IEC 60250
Dielectric constant	at 23 °C at 80 °C	2.65 2.49	IEC 60250 IEC 60250
Water absorption	at 50°C, 42d	0.18%	ISO 62

3M Deutschland GmbH Carl-Schurz-Str.1 41453 Neuss Germany

Reference: AABBDD17680#EN 04

Issue date 07.05.2020 Supersedes: 15.01.2016

### 3.2 Performance Tests

Scotchcast<sup>™</sup> Resin 2123 has been tested with proper cable junction box according to IEC 60529 and meets the requirements of IP 68.

# 4. Usage Information

#### 4.1 Features

- 3M<sup>™</sup> Scotchcast<sup>™</sup> Easy Dispenser 250 is compatible and used with commercially available applicator guns
- Mixing of resin components is by a static mixer and delivered together with cartridge
- Easy re-accessibility of the cable connection
- Homogeneous and reliable insulation
- Good protection against water (IPx8)
- Low exothermic reaction temperature (0.6 °C raise from 24 °C)
- Continuous operating temperature of the resin at 90 °C, emergencies up to 130 °C

## 4.2 Available Sizes

Scotchcast™ Easy Dispenser 250 cartridge: 250 ml

Scotchcast<sup>™</sup> Resin 2123 will be supplied in two-chamber plastic cartridge with a static mixer to ensure a correct mixing ratio for applying the resin. Cartridge can be mounted into commercial available application guns. For humidity protection the cartridge is supplied in an aluminium guard bag which must stay closed until the first use.

## 4.3 Application Condition

Keep cartridges at 5 °C or warmer before mixing. In cooler conditions keep cartridges in warmer area until ready to mix.

# 4.4 Storage Condition and Shelf Life

3M<sup>™</sup> Scotchcast<sup>™</sup> Resin 2123 has a shelf life of 24 months when stored between 10 °C and 40 °C with humidity level < 75 % in the original sealed bag. The expiration date of each product appears on the product packaging.

## 4.5 Safety and Handling

3M provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, storage, use and disposal information. 3M strongly encourages its customers to review the MSDS on its products prior to their use.

3M Deutschland GmbH Carl-Schurz-Str.1 41453 Neuss Germany Reference: AABBDD17680#EN 04 Issue date 07.05.2020 Supersedes: 15.01.2016

# 5. Additional Information

To request additional product information, see address below.

# **Important Notice**

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

Values presented have been determined by standard test methods and are average values not meant to be used for specification purposes.

All questions of warranty and liability relating to 3M products are governed by the terms of the respective sale subject, where applicable, to the prevailing law.

3M is a trademark of the 3M Company.

3M Deutschland GmbH Carl-Schurz-Str.1 41453 Neuss Germany Reference: AABBDD17680#EN 04 Issue date 07.05.2020 Supersedes: 15.01.2016